

# PRODUCT DATA SHEET

## GEOTEX® 315ST

**GEOTEX 315ST** is a woven slit film geotextile produced by Propex, and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. The individual slit films are woven together in such a manner as to provide dimensional stability relative to each other. The construction of the geotextile makes **GEOTEX 315ST** ideal for soil separation and stabilization and meets AASHTO M288 Class I standards. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils.

**GEOTEX 315ST** conforms to the property values listed below.<sup>1</sup> Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

PROPERTY	TEST METHOD	MARV <sup>2</sup>	
		ENGLISH	METRIC
<b>Mechanical</b>			
Tensile Strength (Grab)	ASTM D-4632	315 lbs	1400 N
Elongation	ASTM D-4632	12 %	12 %
Puncture	ASTM D-4833	150 lbs	667 N
CBR Puncture	ASTM D-6241	900 lbs	4000 N
Mullen Burst	ASTM D-3786	600 psi	4137 kPa
Trapezoidal Tear	ASTM D-4533	113 lbs	503 N
<b>Endurance</b>			
UV Resistance % Retained at 500 hrs	ASTM D-4355	70%	70%
<b>Hydraulic</b>			
Apparent Opening Size (AOS) <sup>3</sup>	ASTM D-4751	40 US Std. Sieve	0.425 mm
Permittivity	ASTM D-4491	0.05 sec <sup>-1</sup>	0.05 sec <sup>-1</sup>
Water Flow Rate	ASTM D-4491	4 gpm/ft <sup>2</sup>	160 l/min/m <sup>2</sup>
<b>Roll Sizes</b>		12.5 ft x 360 ft	3.81 m x 109.8 m
		15.0 ft x 300 ft	4.57 m x 91.5 m
		17.5 ft x 258 ft	5.33 m x 78.6 m

### NOTES:

1. The property values listed above are effective 07/2008 and are subject to change without notice.
2. Values reported in weaker principal direction. All values listed are Minimum Average Roll Values (MARV) unless otherwise noted, calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported. Maximum Average Roll Value (MaxARV) is calculated as typical plus two standard deviations.
3. Maximum average roll value.



THE ADVANTAGE CREATORS.™

Propex Inc.  
6025 Lee Highway, Suite 425  
PO Box 22788  
Chattanooga, TN 37422

PH: 423 899 0444  
PH: 800 621 1273  
FAX: 423 899 7619  
www.geotextile.com

Geotex®, Landlok®, Pyramat®, X3®, SuperGro®, Petromat® and Petrotac® are registered trademarks of Propex Inc.

THIS PUBLICATION SHOULD NOT BE CONSTRUED AS ENGINEERING ADVICE. WHILE INFORMATION CONTAINED IN THIS PUBLICATION IS ACCURATE TO THE BEST OF OUR KNOWLEDGE, PROPEX DOES NOT WARRANT ITS ACCURACY OR COMPLETENESS. THE ULTIMATE CUSTOMER AND USER OF THE PRODUCTS SHOULD ASSUME SOLE RESPONSIBILITY FOR THE FINAL DETERMINATION OF THE SUITABILITY OF THE INFORMATION AND THE PRODUCTS FOR THE CONTEMPLATED AND ACTUAL USE. THE ONLY WARRANTY MADE BY PROPEX FOR ITS PRODUCTS IS SET FORTH IN OUR PRODUCT DATA SHEETS FOR THE PRODUCT, OR SUCH OTHER WRITTEN WARRANTY AS MAY BE AGREED BY PROPEX AND INDIVIDUAL CUSTOMERS. PROPEX SPECIFICALLY DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ARISING FROM PROVISION OF SAMPLES, A COURSE OF DEALING OR USAGE OF TRADE.