



**GEOTEX 200ST** is a woven polypropylene geotextile containing heavy woven flat tape yarns produced by Propex, and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. These characteristics make **GEOTEX 200ST** ideal for the construction of embankments over soft soils, steepened slopes, and modular block and/or wrapped-face retaining walls. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils.

**GEOTEX 200ST** conforms to the property values listed below<sup>1</sup>, as well as meets the requirements set forth by AASHTO M-288/NTPEP (Geotextile Specification for Highway Application). Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP). This product is NTPEP approved for AASHTO standards.

MARV<sup>2</sup>

PROPERTY	TEST METHOD	ENGLISH	METRIC
<b>ORIGIN OF MATERIALS</b>			
% U.S. Manufactured Inputs		100%	100%
% U.S. Manufactured		100%	100%
<b>MECHANICAL</b>			
Tensile Strength (Grab)	ASTM D-4632	200 lbs	890 N
Elongation	ASTM D-4632	15%	15%
CBR Puncture	ASTM D-6241	700 lbs	3115 N
Trapezoidal Tear	ASTM D-4533	75 lbs	333.8 N
<b>ENDURANCE</b>			
UV Resistance % Retained at 500 hrs	ASTM D-4355	70%	70%
<b>HYDRAULIC</b>			
Apparent Opening Size (AOS) <sup>3</sup>	ASTM D-4751	40 US Std. Sieve	0.425 mm
Permittivity	ASTM D-4491	0.05 sec <sup>-1</sup>	0.05 sec <sup>-1</sup>
Water Flow Rate	ASTM D-4491	4 gpm/ft <sup>2</sup>	163 lpm/m <sup>2</sup>
ROLL SIZES		12.5 ft x 432 ft	3.81 m x 131.7 m
		15.0 ft x 360 ft	4.57 m x 109.7 m
		17.5 ft x 309 ft	5.33 m x 94.2 m

**NOTES:**

1. The property values listed above are effective 04/2011 and are subject to change without notice.
2. Values shown are in weaker principal direction. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported.
3. Maximum average roll value.



TESTED. PROVEN. TRUSTED.  
[www.geotextile.com](http://www.geotextile.com)

**Propex Operating Company, LLC** · 6025 Lee Highway, Suite 425 · PO Box 22788 · Chattanooga, TN 37422

ph 423 899 0444 · ph 800 621 1273 · fax 423 899 7619

Geotex<sup>®</sup>, Landlok<sup>®</sup>, Pyramat<sup>®</sup>, X3<sup>®</sup>, SuperGro<sup>®</sup>, Petromat<sup>®</sup> and Petrotac<sup>®</sup> are registered trademarks of Propex Operating Company, LLC.

This publication should not be construed as engineering advice. While information contained in this publication is accurate to the best of our knowledge, Propex does not warrant its accuracy or completeness. The ultimate customer and user of the products should assume sole responsibility for the final determination of the suitability of the information and the products for the contemplated and actual use. The only warranty made by Propex for its products is set forth in our product data sheets for the product, or such other written warranty as may be agreed by Propex and individual customers. Propex specifically disclaims all other warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, or arising from provision of samples, a course of dealing or usage of trade.